
 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های رو زمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادر کننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PL</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PL	RT	0001	D04	شماره صفحه : ۱ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PL	RT	0001	D04																			

طرح نگهداشت و افزایش تولید ۲۷ مخزن

PIPING CORROSION STUDY & MATERIAL SELECTION REPORT

نگهداشت و افزایش تولید میدان نفتی بینک



D04	JAN. 2023	AFD	M.Noori	M.Fakharian	M. Mehrshad	
D03	OCT. 2022	AFD	M.Noori	M.Fakharian	M. Mehrshad	
D02	AUG. 2022	AFD	F.Mosayebnejad	M.Fakharian	M. Mehrshad	
D01	MAR. 2022	IFA	A.Khosravi	M.Fakharian	M. Mehrshad	
D00	NOV. 2021	IFC	H.Shahrokhi	M.Fakharian	M. Mehrshad	
Rev.	Date	Purpose of Issue/Status	Prepared by:	Checked by:	Approved by:	CLIENT Approval

Class:2

CLIENT Doc. Number: 'F0Z-707359

Status:



IDC: Inter-Discipline Check
 IFC: Issued For Comment
 IFA: Issued For Approval
 AFD: Approved For Design
 AFC: Approved For Construction
 AFP: Approved For Purchase
 AFQ: Approved For Quotation
 IFI: Issued For Information
 AB-R: As-Built for CLIENT Review
 AB-A: As-Built –Approved

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																	
شماره پیمان:	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT	شماره صفحه ۲: از ۲۵																
۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><td>پروژه</td><td>بسته کاری</td><td>صادر کننده</td><td>تسهیلات</td><td>رشته</td><td>نوع مدرک</td><td>سریال</td><td>نسخه</td></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه											
BK	SSGRL	PEDCO	110	PI	RT	0001	D04											

REVISION RECORD SHEET





PAGE	D00	D01	D02	D03	D04
1	x	x	x	x	x
2	x	x	x	x	x
3	x				
4	x				
5	x	x			
6	x	x			
7	x				
8	x				
9	x				
10	x				
11	x				
12	x				
13	x				
14	x				
15	x				
16	x				
17	x				
18	x				
19	x			x	
20	x	x	x		
21	x	x	x		
22		x	x		
23		x	x		
24			x		x
25				x	
26					
27					
28					
29					
30					
31					
32					
33					
34					
35					
36					
37					
38					
39					
40					
41					
42					
43					
44					
45					
46					
47					
48					
49					
50					
51					
52					
53					
54					
55					
56					
57					
58					
59					
60					
61					
62					
63					
64					
65					

PAGE	D00	D01	D02	D03	D04
66					
67					
68					
69					
70					
71					
72					
73					
74					
75					
76					
77					
78					
79					
80					
81					
82					
83					
84					
85					
86					
87					
88					
89					
90					
91					
92					
93					
94					
95					
96					
97					
98					
99					
100					
101					
102					
103					
104					
105					
106					
107					
108					
109					
110					
111					
112					
113					
114					
115					
116					
117					
118					
119					
120					
121					
122					
123					
124					
125					
126					
127					
128					
129					
130					

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه: ۳ از ۲۵
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

CONTENTS

1. INTRODUCTION	4
2. SCOPE	5
3. NORMATIVE REFERENCES	5
3.1 LOCAL CODES AND STANDARDS	5
3.2 INTERNATIONAL CODES AND STANDARDS	5
3.3 THE PROJECT DOCUMENTS	5
3.4 ENVIRONMENTAL DATA	6
3.5 UNITS OF MEASUREMENTS AND ABBREVIATIONS	6
3.6 ORDER OF PRECEDENCE	7
4. PREDICTION OF CORROSION AND DEGRADATION MODES	7
4.1 GENERAL	7
4.2 PRESENCE OF WATER	7
4.3 CO ₂ CORROSION	8
4.4 H ₂ S CORROSION	8
4.5 CORROSION CALCULATION SOFTWARE	10
4.6 CRACKING GENERAL	10
4.7 CHLORIDE INDUCED STRESS CORROSION CRACKING (CSCC)	12
4.8 LOW TEMPERATURE SERVICE	13
4.9 ORGANIC ACIDS	13
4.10 UNDER DEPOSIT CORROSION	13
4.11 OXYGEN CORROSION	13
4.12 MICROBIOLOGICALLY INDUCED CORROSION (MIC)	14
4.13 ELEMENTAL SULPHUR CORROSION	14
4.14 CHEMICAL CORROSION	14
5. MATERIALS SELECTION PHILOSOPHY	15
5.1 MATERIALS SELECTION OPTIONS	15
5.2 CANDIDATE MATERIALS	15
6. CORROSION ASSESSMENT	18
6.1 GENERAL	18
6.2 CORROSIVE SPECIES: CO ₂ AND H ₂ S	18
6.3 CORROSION ASSESSMENT – UNINHIBITED FLUID	18
6.4 CORROSION MONITORING PHILOSOPHY	18
7. HYDROCARBON , WATER CHARACTERISTICS	19
7.1 OIL COMPOSITION	19
7.2 FORMATION WATER	19
8. RECOMMENDATION	20
8.1 PROCESS EQUIPMENT	20
8.2 PROCESS PIPING	20
8.3 UTILITY PIPING	24
9. ATACHMENTS	25

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>	 شرکت توسعه و پارس  HIRGAN ENERGY 																								
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادر کننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	شماره صفحه : ۴ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

1. INTRODUCTION

Binak oilfield in Bushehr province is a part of the southern oilfields of Iran, is located 20 km northwest of Genaveh city.



With the aim of increasing production of oil from Binak oilfield, an EPC/EPD Project has been defined by NIOC/NISOC and awarded to Petro Iran Development Company (PEDCO). Also PEDCO (as General Contractor) has assigned the EPC-packages of the Project to "Hirgan Energy - Design and Inspection" JV.

As a part of the Project, construction of well location, access roads, wellhead facilities for 6 new wells (with electric power supply for 2 of them) and required modifications on 4 workover wells (with electric power supply) shall be done. In addition, construction of 6 new flowlines from new wells to Binak B/C unit (with extension of relevant manifold) are in the Project scope of work.

GENERAL DEFINITION

The following terms shall be used in this document.

CLIENT:	National Iranian South Oilfields CLIENT (NISOC)
PROJECT:	Binak Oilfield Development – Construction of New Well Locations, Modifications on Workover Wells, Wellhead Facilities, Electrification Facilities, Flowlines and Extension of Binak B/C Manifold
EPD/EPC CONTRACTOR (GC):	Petro Iran Development Company (PEDCO)
EPC CONTRACTOR:	Joint Venture of : Hirgan Energy – Design & Inspection (D&I) Companies
VENDOR:	The firm or person who will fabricate the equipment or material.
EXECUTOR:	Executor is the party which carries out all or part of construction and/or commissioning for the project.
THIRD PARTY INSPECTOR (TPI):	The firm appointed by EPD/EPC CONTRACTOR (GC) and approved by CLIENT (in writing) for the inspection of goods.
SHALL:	Is used where a provision is mandatory.
SHOULD:	Is used where a provision is advisory only.
WILL:	Is normally used in connection with the action by CLIENT rather than by an EPC/EPD CONTRACTOR, supplier or VENDOR.
MAY:	Is used where a provision is completely discretionary.

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه: ۵ از ۲۵
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

2. SCOPE

This document details the procedures used to corrosion study and material selection of inside plant of BINAK new wellhead facilities and manifold extension with all necessary equipment and piping.

3. NORMATIVE REFERENCES

3.1 LOCAL CODES AND STANDARDS



- IPS G-ME-150 Iranian Petroleum Standard – Engineering & Material Standard for Towers , Reactors, Pressure vessels & Internals
- IPS-I-TP-802 Inspection standard for corrosion survey and inhibitor evaluation
- IPS-E-TP-100 Engineering Standard for Paints
- IPS-E-TP-350 Engineering Standards for Linings.
- IPS-E-TP-740 Engineering Standard for Corrosion Considerations in Material Selection
- IPS-E-TP-780 Engineering Standards for Chemical Control of Corrosion Environments

3.2 INTERNATIONAL CODES AND STANDARDS

- NACE MR 0175 / ISO 15156 Petroleum and Natural Gas Industries - Materials for use in H₂S containing Environments in Oil and Gas Production
- API 5L Specification for Line Pipe
- DNV RP 0501 Erosive wear in piping systems
- ASME SA 578 Standard Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications

3.3 THE PROJECT DOCUMENTS

- BK-GNRAL-PEDCO-000-PR-DB-0001 Process Basis of Design

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های رو زمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><td>پروژه</td><td>بسته کاری</td><td>صادر کننده</td><td>تسهیلات</td><td>رشته</td><td>نوع مدرک</td><td>سریال</td><td>نسخه</td></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	شماره صفحه: ۶ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

- BK-SSGRL-PEDCO-110-PI-SP-0001 Piping Material Specification
- BK-GNRAL-PEDCO-000-PI-SP-0006 Specification for Painting
- BK-GNRAL-PEDCO-000-PI-SP-0008 Specification For Material Requirements in Sour service
- BK-W007S-PEDCO-110-PR-PF-0001 Process Flow Diagrams-Extension of BINAK B/C
- BK-W007S-PEDCO-110-PR-PF-0002 Process Flow Diagrams-W007S
- BK-W008N-PEDCO-110-PR-PF-0001 Process Flow Diagrams-W008N
- BK-W018S-PEDCO-110-PR-PF-0001 Process Flow Diagrams-W018S
- BK- W035-PEDCO-110-PR-PF-0001 Process Flow Diagrams-W035
- BK- W028-PEDCO-110-PR-PF-0001 Process Flow Diagrams-W028
- BK- W046S-PEDCO-110-PR-PF-0001 Process Flow Diagrams-W046S



3.4 ENVIRONMENTAL DATA

Refer to "Process Basis of Design; Doc. No. BK-GNRAL-PEDCO-000-PR-DB-0001".

3.5 UNITS OF MEASUREMENTS AND ABBREVIATIONS

SI unit of measurements is used in the whole documents unless noted otherwise and the following abbreviations are used in this document:

- bbl/day Barrels of Liquid per Day
- BOPD Barrels of Oil per Day
- CA Corrosion Allowance
- CR Corrosion Rate
- MMSCFD Million Standard Cubic Feet per Day
- PPM Parts Per Million
- TOL Top of Line
- BOL Bottom of Line
- GOR Gas Oil Ratio
- Cl Chloride
- CRA Corrosion Resistant Alloy
- SCC Stress Corrosion cracking

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>								
شماره پیمان:	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه: ۷ از ۲۵	
۰۵۳ - ۰۷۳ - ۹۱۸۴	پروژه	بسته کاری	صادرکننده	تسهیلات	رشته	نوع مدرک	سریال		نسخه
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	

- HIC hydrogen-induced cracking
- SWC Stepwise Cracking
- SLC Service Life Corrosion
- CMP Corrosion Management Program

3.6 ORDER OF PRECEDENCE

In case of any conflict between requirements specified herein & the requirements of any other referenced document, this subject shall be reflected to CLIENT and the final decision will be made by CLIENT.

4. PREDICTION OF CORROSION AND DEGRADATION MODES

4.1 GENERAL



Corrosion risks must consider the range of operating conditions over the field life, including start up and shutdown as well as high flow and low flow and the full range of temperatures that can be experienced either due to operating conditions, and /or environmental temperatures and blow down. Where corrosion cannot be mitigated by carbon steel with inhibition, Corrosion Resistant Alloys (CRA) may be selected. The selection of the type of CRA will be influenced by additional factors including pH, partial pressure H₂S, Cl content, temperature, etc.

The following sections on CO₂ and H₂S corrosion deal with corrosion mechanisms on carbon steels.

4.2 PRESENCE OF WATER

The presence of water is the crucial factor in the assessment of corrosion risks to Hydrocarbon production systems. Hydrocarbon flows on their own are non-corrosive towards carbon steel and do not pose corrosion risk. However, if water is present in the form of liquid water it can dissolve CO₂ and H₂S contained in the produced fluids to form acidic solutions that then lead to corrosion of the metallic materials used to retain them.

Water may be present as formation water, produced along with the hydrocarbons from the reservoir itself, or be present as water of condensation which will condense out from the water saturated Hydrocarbons as the produced fluids cool or due to pressure drop. The formation water analysis has been taken from the Process Basis of Design with document No. BK-GNRAL-PEDCO-000-PR-DB-0001. The formation water is reported as containing up to 127800 ppm. The influence of Cl is discussed below and has a major effect on the stability of the Iron Sulphide (FeS) scale leading to breakdown and pitting under certain circumstances. Chloride in combination with H₂S also plays a major role in the Sulphide Stress Corrosion Cracking of Corrosion Resistant Alloys.

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادرکننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادرکننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	شماره صفحه: ۸ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادرکننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

Bicarbonate is beneficial in the corrosion process and increases the pH which has been lowered by the CO₂ and H₂S gasses. Reductions in corrosion rate associated with bicarbonate ions can only be considered where water is comprised of formation water. Water of condensation does not contain bicarbonate and therefore its effect on pH cannot be considered in these lines.

Corrosion in Oil and multiphase lines is dependent on flowing conditions and also the ability of the oil to retain water in suspension and for the pipe walls to be continually oil wetted. This in turn relies on the water cut and the density and viscosity of the oil.

4.3 CO₂ CORROSION

CO₂ corrosion is a common failure mode in hydrocarbon production facilities. The corrosion is caused by CO₂ dissolving in the water phase to form carbonic acid, which is corrosive to carbon steel. Based on API 571 Section 4-80, increasing the level of chromium in steels offers no major improvement in resistance until a minimum of 12% is reached.

However, the presence of H₂S in the fluids may strongly affect CO₂ corrosion. There are three different practical corrosion domains of carbon steel to consider. These are dependent on the proportions of CO₂ and H₂S in the fluids:

Partial Pressure Ratio	Corrosion Domain
CO ₂ / H ₂ S > 500	CO ₂ corrosion dominates
500 ≥ CO ₂ /H ₂ S ≥ 20	Mixed CO ₂ / H ₂ S corrosion
CO ₂ / H ₂ S < 20	H ₂ S corrosion dominates



For BINAK Production wells, the high H₂S case results in an H₂S dominant domain.

All of the traditional corrosion calculation models which are available are based on the well-established De Waard and Milliams equations, which were developed for evaluation of CO₂ corrosion. The majority of these programs are not able to consider the influence of H₂S in the corrosion rate calculations and tend to overestimate general corrosion when compared to actual corrosion test data and operational experience.

4.4 H₂S CORROSION

The Iron Sulphide (FeS) film formed by aqueous H₂S in contact with steel surfaces is a relatively hard corrosion product and is normally tightly adhere to the surface of the steel. This is in contrast to the iron carbonate scale formed under CO₂ dominant systems which is relatively soft and can easily be removed by erosion. This hard adherent FeS scale has been shown to prevent general corrosion and general weight loss corrosion is rarely a problem in carbon steel equipment.

The FeS scale prevents the traditional general weight loss type of CO₂ corrosion, in combined

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه: ۹ از ۲۵
	پروژه	بسته کاری	صادرکننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

CO₂ / H₂S systems, even with significant levels of CO₂. The major impact of the CO₂ in an H₂S dominant system is to combine with the H₂S to further reduce the PH. As the pH is reduced, the stability of the FeS scale can be compromised and local breakdown may lead to pitting corrosion.

The complex interaction of Iron Sulphide corrosion product films and process parameters such as flow rate, flow regime, solids, and pH and chloride contents can cause large changes to the characteristics of the Iron Sulphide film, and the level of protection it provides.

Under field conditions it can be assumed that pitting corrosion may occur at locations where the surface film is stressed e.g. by locally high flow velocities or in locations with lowered pH like stagnant water phase in dead legs, or at low points in pipelines flowing at low velocities, or under deposits.

For oil wetted pipes TOL is not considered a major problem unless there is a high GOR and laminar flow with high condensation rates. However it is a consideration for the gas overhead lines. Where predicted corrosion levels are not high, carbon steel can be considered as a suitable selection provided that the wall of the pipe is maintained above the dew point by insulation and heat tracing. This option has been used on several projects to avoid the cost of more expensive CRA options.

➤ DOMAINS OF SOUR SERVICE

Domains of sour service are defined in Figure 1, showing four Regions characterizing materials suitability for sour service applications as per NACE MR 0175/ ISO 15156. These are:



Region 0: "Sweet Service" (only negligible traces of H₂S): the domain within which no specific metallurgical precautions are needed. This Region applies to all metallic components.

Region 1: "Mild Sour Service" The domain within which minor and inexpensive precautions is required. An example of materials which can be used within Region 1 includes carbon steel tubing and casing up to API 5 CT grades P110 - this Region applies to any material of similar sensitivity to SSC.

Region 2: "Intermediate Sour Service" The domain within which increasing precautions are required. An example of materials, which can be used within Region 2, includes carbon and low alloy steel tubing and casing up to the API 5CT grade N80. This Region applies to any material of similar sensitivity to SSC.

Similarly, resistance to HIC and SOHIC can be achieved by the use of moderately low sulphur, clean and micro structurally homogeneous steels.

Region 3: "Severe Sour Service" The domain within which the most stringent precautions are necessary. Examples include materials taken from the ISO 15156 reference list. Similarly,

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادر کننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	شماره صفحه : ۱۰ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

resistance to SWC requires steels with very low sulphur and other impurity contents, and/or calcium treatment, and qualified by laboratory testing in the expected service conditions.




Figure 1 - Limits of sour service



The domain of crude oil services with H₂S mole percentage and calculated PH have been specified region 1,2,3 as per as per section 8.

4.5 CORROSION CALCULATION SOFTWARE

The ECE 5.4 program specifically considers the impact of H₂S along with the factors described above for CO₂ corrosion. ECE 5.4 considers the beneficial effect of the FeS scale in preventing general corrosion but also advises the risks of pitting in wet sour service. The pit depths predicted by the program are approximately related to CO₂ corrosion rates as described above. ECE 5.4 has been widely used for the estimation of corrosion in sour systems and in the case of this project it has been used as the basis for the corrosion rate calculations. ECE 5.4 also has a module termed the Alloy Selector which provides guidance on selection of CRA's and Nickel (Ni) based alloys for sour and sweet service based on temperatures and partial pressures of CO₂ and H₂S and Cl levels. This module is generally in alignment with NACE MR0175/ISO 15156 and was developed based on a wide range of corrosion data. It provides guidance on the avoidance of corrosion and environmental cracking. The ECE 5.4 program has predicted pitting corrosion with low levels of general corrosion. However, this software specifies NACE MR 0175/ISO15156 regions accurately.

4.6 CRACKING GENERAL

The presence of H₂S can also give rise to three principal types of cracking in steels. These are Sulphide Stress Corrosion cracking (SSCC), which may occur in carbon, low alloy, and stainless steels, and hydrogen-induced cracking (HIC), which is limited to carbon and low alloy steels, and Stepwise Cracking (SWC).

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه : ۱۱ از ۲۵
	پروژه	بسته کاری	صادرکننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

4.6.1 SULPHIDE STRESS CORROSION CRACKING (SSCC)

Sulphide Stress Corrosion Cracking (SSCC) results from the joint action of corrosion and tensile stress (residual or applied) in the presence of water and H₂S.

SSCC occurs when atomic hydrogen released during a corrosion process in H₂S containing solutions diffuses into the metal but remains in solid solution in the crystal lattice. This reduces the ductility and deformability of the metal, particularly untempered Martensitic, which already has limited ductility. Under tensile stress, whether applied or residual from cold forming or welding, this embrittled metal readily cracks to form sulphide stress cracks. The cracking process is very rapid and has been known to take as little as a few hours for a crack to form and cause catastrophic failure.

Stress corrosion cracking not only affects carbon steel and low alloy steel but also occurs in Corrosion Resistant Alloys (CRAs). In the presence of chlorides austenitic and duplex stainless steels are also susceptible to stress corrosion cracking in H₂S environments. Increasing the nickel content in CRAs improves the resistance to SSCC and in general, alloys with in excess of 40 % Ni are immune to SSC in the presence of Cl and H₂S.



The limitation for the safe use of CRAs is dependent upon several contributory factors such as the partial pressure of the H₂S, the level of chlorides, the partial pressure of CO₂, and system PH. Guidance for use of carbon steels and CRAs in H₂S containing environments are spelt out in tabular forms in NACE MR0175/ISO 15156, under H₂S conditions.

4.6.2 HYDROGEN INDUCED CRACKING (HIC)

Hydrogen Induced Cracking (HIC) principally affects rolled carbon and low alloy steel products, whereby any atomic hydrogen produced from the corrosion reaction diffuses into the steel and accumulates around non-metallic inclusions in the steel. The hydrogen atoms recombine as molecular hydrogen at trap sites in the steel matrix. Favorable trap sites are typically found in rolled products along elongated inclusions or segregated bands of microstructure. The high pressures generated result firstly in a crack initiation phase and then propagation along the metallurgical structure sensitive to this type of hydrogen embitterment. As more hydrogen enters the voids the pressure rises, deforming the surrounding steel so that blisters may become visible at the surface. Sulphur content in the plate material shall not exceed 0.003%, the cleanliness of the steel play an important role in the mitigation of HIC.

4.6.3 STEPWISE CRACKING (SWC)

Stepwise cracking occurs following hydrogen charging. Where steel around HIC cracks becomes highly strained, can causing linking of adjacent cracks to form stepwise cracking, so called because the arrays of cracks have a stepwise appearance.

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							 شماره صفحه : ۱۲ از ۲۵
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

There is no lower acceptable limit. For the partial pressure of H₂S that can be considered safe to prevent the onset of HIC/SWC damage, however it is rarely a problem of practical significance at partial pressures below 3.5 mbar.

HIC/SWC can be controlled by modification of the chemical composition of the materials. The specific requirements are spelt out in ISO 15156. Testing and acceptance criteria shall be addressed in the Project Materials Specifications.

4.6.4 GALVANIC HYDROGEN STRESS CRACKING (GHSC)

Galvanic corrosion (GHSC) can be a concern when dissimilar materials are in contact in a conductive fluid such as an H₂S environment.



When two different metallic materials are electrically connected and placed in a conductive solution (electrolyte), an electric potential exists. This potential difference will provide a stronger driving force for the dissolution of the less noble (more electrically negative) material.

Preventive measures that may be taken include:

1. When joining two dissimilar metals together, galvanic corrosion can be prevented by insulating the two materials from each other. For example, when bolting flanges of dissimilar metals together, plastic washers can be used to separate the two metals.
2. Do not couple metals that are far apart in the galvanic series.
3. Avoid small anode–large cathode combinations. Fasteners should be cathodic to the parts being fastened.
4. Any coating being applied should be applied to the cathodic member and not to the anodic member. This is to prevent an unfavorable anode/cathode ratio should any discontinuity in the coating occur.
5. Anodic parts may be made thicker to provide a longer life.
6. A sacrificial metal may be installed that would be anodic to both metals.

4.7 CHLORIDE INDUCED STRESS CORROSION CRACKING (CSCC)

Austenitic and duplex stainless steels may suffer from external Chloride Induced Stress Corrosion Cracking (CSCC) when exposed to a combination of tensile stresses, chlorides, water, oxygen, and elevated temperature. This failure mode, typically caused by exposure to humid marine atmosphere, may represent a higher risk than the internal service and is generally manifested by a sudden fracture of pipe or equipment.

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه : ۱۳ از ۲۵
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

Where external CSCC is considered a possibility, susceptible materials can be coated with a high integrity organic coating system or Thermally Sprayed Aluminum (TSA). Alternatively, alloy with greater resistance to CSCC may be selected.

4.8 LOW TEMPERATURE SERVICE

The materials selection process shall consider the Minimum Design Material Temperature (MDMT) for all piping and equipment, determined in accordance with the applicable codes and standards. All materials shall have adequate low temperature toughness to prevent brittle fracture during normal operation and under blow down load conditions.

For carbon steel vessels actual stresses at the minimum temperature shall be taken into consideration when deciding the material test temperatures, in accordance with the design codes. Use of thermal sleeves and local use of austenitic materials for local "cold spots" shall be considered if required.

Materials shall follow the requirements of ASME VIII and B31.3 in addition to the project Equipment data sheets and piping classes, based upon the minimum anticipated metal skin temperature and wall thickness.

4.9 ORGANIC ACIDS

Minor amounts of organic acids, primarily acetic acid, but also formic may also be present and can influence and complement corrosion by lowering the pH and supplying more H⁺ ions for reaction. They can also prevent formation and interfere with the protectiveness of carbonate and iron sulphide scales. However there is no reference to these acids in the basis of design.



4.10 UNDER DEPOSIT CORROSION

During periods of low flow, such as startup and shut down, it is possible for deposits to settle out of wet sour gas streams onto the bottom of piping and cause under deposit corrosion. Corrosion occurs due to a form of crevice corrosion initiated by a difference in acid water concentration under the deposit. The deposit also prevents wetting of the steel surface by corrosion inhibitor leaving localized areas unprotected.

Deposits of solids may also act as sites for sulphate reducing bacteria to accumulate, breed and cause localized corrosion. The bacteria reduce sulphate ions present in the water to sulphide ions that can then cause corrosion problems associated with H₂S. Such bacteria can become very active in de-aerated water.

4.11 OXYGEN CORROSION

Oxygen is not normally present in the production fluids and if detected in the process streams is an indication of an operational upset. Every effort shall be made to exclude oxygen as it has potentially serious consequences on the corrosion resistance of metallic materials.

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه : ۱۴ از ۲۵
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

It greatly increases the tendency towards pitting of carbon steels and CRAs in these environments and greatly increases the likelihood of stress corrosion cracking of CRAs.

Water used for water injection can be either deaerated or aerated, which will have an impact on the corrosivity. Due to the removal of oxygen in deaerated water, the corrosion rate of carbon steel will be low, whereas in systems carrying aerated water a higher corrosion rate must be anticipated. Oxygen corrosion is a time dependent corrosion mechanism and takes principally the form of uniform corrosion, but localized attacks may also occur pitting.

4.12 MICROBIOLOGICALLY INDUCED CORROSION (MIC)

Sulfate Reducing Bacteria (SRB) are the major contributors to microbiological induced corrosion for the inside of oil and gas producing facilities. As a result of the reduction of sulfates, hydrogen sulfide is created by the bacteria. Locally, under the colonies of bacteria, iron is bound to iron-sulfide. The result can be severe pitting corrosion.

SRB's are normally not present in an oil well and downstream production facilities, unless introduced by man e.g. During hydrotesting or together with injection or wash-water. Process wash water is fresh water produced by passing raw water through deaeration package. The deaerated water is treated with biocides. Because biocides are injected at 2 types (A & B), the total amount of active(live) bacteria in the system will be small.



4.13 ELEMENTAL SULPHUR CORROSION

At present there is only a limited amount of information available regarding the presence of elemental sulphur in the well stream fluids. If present, contamination of the production fluids is particularly deleterious because of its influence on pitting corrosion mechanisms discussed earlier under H₂S corrosion. Sulphur is naturally soluble in liquid hydrocarbons where it does not present a corrosion threat. However, when it has been encountered in hydrocarbon systems it accelerates pitting corrosion rates in carbon steels. CRAs generally suffer localized corrosion in the presence of elemental sulphur and it can be deleterious on the corrosion resistance of most CRA's.

4.14 CHEMICAL CORROSION

As the chemical compositions are in accordance with vendor proficiency then following survey have been done as per vendor recommendation.

Oxygen Scavenger is an ammonium bisulfate based that used to remove dissolved oxygen from water in oil field and water injection systems. Oxygen Scavenger is water soluble which is corrosive on carbon steel material then for this case stainless steel material shall be selected for handling, storage and piping system. PH for Oxygen Scavenger is near 4.

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادر کننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	شماره صفحه : ۱۵ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

Demulsifier is a blend of complex surface active compounds, formulated to give a product capable of improved hydrocarbon recovery from crude oil emulsion. Demulsifier gives a rapid water separation, reduces salt content of treated crude oil and minimize hydrocarbon level in dump water. Demulsifier is aromatics soluble.

Scale inhibitor is a highly effective organ phosphorous compound designed to control scale formation in water injection, salt water disposal systems and in downhole pumping equipment. Although this is effective for continuous injection in surface facilities. Scale inhibitor is soluble in fresh water and brines which is corrosive on carbon steel material then for this case stainless steel material shall be selected for handling, storage and piping system. PH for scale inhibitor is less than 2.

Corrosion Inhibitor is prevention of corrosion in oil wells and flow lines with high water content. Corrosion Inhibitor is water soluble. PH for Corrosion Inhibitor is near 4. Corrosion Inhibitor is corrosive on carbon steel material then for this case stainless steel material shall be selected for handling, storage and piping system.

Biocide is a highly effective against both aerobic and anaerobic microorganisms such as SRB. Biocide is water soluble. PH for biocide is between 2.5-4.5. Biocide is corrosive on carbon steel material then for this case stainless steel material shall be selected for handling, storage and piping system.

Liquid Reverse Demulsifier is a cationic charged. The main application for Liquid Reverse Demulsifier is for waste water treatment in oil industry. It is of low viscosity as supplied, and if required can be readily pumped. Reverse Demulsifier is water soluble. PH is near 2. Reverse Demulsifier is corrosive on carbon steel material. If there are not chloride ions in composition, then stainless steel material shall be selected for handling, storage and piping system.



5. MATERIALS SELECTION PHILOSOPHY

5.1 MATERIALS SELECTION OPTIONS

If the total calculated corrosion in the design 20 years life period is less than 1 mm, carbon steel with 1 mm corrosion allowance, if the total calculated corrosion in the design 20 years life period is selected greater than 1mm and less than 3 mm, carbon steel with 3 mm corrosion allowance is selected, if the total calculated corrosion in the design 20 years life period is greater than 3 mm and less than 6 mm then CS with 6 mm CA shall be selected and where Service Life Corrosion (SLC) greater than 6 mm CA or high pitting corrosion rate, the solid or cladding Corrosion Resistant Alloys (CRA) are selected.

5.2 CANDIDATE MATERIALS

The levels of H₂S in the majority of streams, together with the corrosively of the associated CO₂ levels, mean that the H₂S partial pressure has dominated material selection. Nickel based alloys

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه: ۱۶ از ۲۵
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

have the highest tolerance to wet H₂S in the presence of wet H₂S, while the stainless steel have a smaller, but significant tolerance. Carbon steels can have excellent tolerance to wet H₂S, but suffer badly from wet CO₂ corrosion, limiting their application. As tolerance to H₂S increases with price, it follows that the most economical solution is to select the lowest grade of materials which will tolerate the relevant conditions.

The material considered for selection is summarized in the following sub-sections. The materials mentioned are in contact with the mild aggressive fluid, so the selected material will be carbon steel with NACE requirements for crude oil and for chemical fluid stainless steel will be used.

5.2.1 CARBON STEEL

Carbon Steel is preferred for piping and equipment, as it is cheap and readily available, and its corrosion resistance in wet CO₂ and H₂S conditions is not perceptibly dependent on the levels of chlorides ions in the solution. Low temperature carbon steel with appropriate Charpy toughness shall be used where the design temperature is below -29 °C and down to -45 °C.

Corrosion by wet CO₂ and H₂S, both limit the application of carbon steel. As resistance to attack by H₂S is dependent on the hardness and cleanliness of the steel, every precaution shall be taken to specify this, consequently SSCC and HIC resistant carbon steel has been specified in the most the applications. Carbon steel hasn't been selected for any application where the (ECE 5.4) predicted the corrosion rate higher than 6 mm or high pitting corrosion rate.



In non-corrosive services carbon steel is suitable material such as instrument air.

5.2.2 316/316L STAINLESS STEEL

This materials is an iron-based alloy with addition of at least 16 % chromium, 10% nickel and 2% molybdenum, it is resistant to wet CO₂ corrosion, but it is susceptible Sulphite Stress Corrosion Cracking (SSCC) at relatively wet low H₂S partial pressures. Its tolerance to wet H₂S is reduced further by the presence of chlorides.

The L indicates a low carbon content to optimize weld corrosion resistance, but it tends to reduce the allowable design stresses. The disadvantage of 316L is the risk of chlorides stress corrosion cracking when it is exposed to atmospheric chlorides at temperatures exceeding 60° C.

The stainless steel materials are suitable for some chemical services such as corrosion inhibitor, demulsifier.

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>							
شماره پیمان:	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه: ۱۷ از ۲۵
۰۵۳ - ۰۷۳ - ۹۱۸۴	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04

5.2.3 Glass –Reinforced Epoxy

GRE is a composite material made of an epoxy resins reinforced by fine fibers made of glass. In principle, GRE is ideal material for handling corrosive fluids, as they do not corrode and are not susceptible to stress-corrosion cracking from either chloride or sulphides. However, their performance is both time-and temperature dependent, as the binders will deteriorate slowly, and this limits their applications to lower temperature than those experienced by many of the materials listed above. The main drawbacks is vulnerability to mechanical damage (which means that they need mechanical protector) and the need for fitting which (unlike straight pipe) have to be laid up by hand, making them both slow and expensive to produce. Consequently, GRE pipe is prime candidate material for long buried pipe runs, where corrosion resistant alloy materials would be expensive and carbon steel would need inhibition and for salty waste water and water lines from 3 phase separators.



As these are relatively new materials, there are constant developments both in binder technology and jointing systems, so that the application limits in terms of operating temperatures and pressure, and the pipe sizes are regularly expanded. Confirmation of the use of GRE to any particular service will depend therefore, on the final design conditions, as the major of grades available are limited to design temperature and pressure. Now we use GRE pipe for underground and aboveground waste water system.

5.2.4 Duplex Stainless Steel

Duplex stainless steels have about 21-27% chromium, 1.7-3.5% molybdenum, and 4-6.5% nickel designed for demanding applications which require exceptional strength and corrosion resistance, it has excellent resistance to chlorides stress corrosion cracking, high thermal conductivity and low coefficient of thermal expansion. The high chromium, molybdenum and nitrogen levels provide excellent resistance to pitting, crevice and general corrosion.

5.2.5 Super Duplex Stainless Steel

Super duplex stainless steels have about 24-26% chromium, 3-5% molybdenum, and 6-8% nickel designed for demanding applications which require exceptional strength and corrosion resistance, it has excellent resistance to chlorides stress corrosion cracking, high thermal conductivity and low coefficient of thermal expansion. The high chromium, molybdenum and nitrogen levels provide excellent resistance to pitting, crevice and general corrosion. Super duplex stainless steels shall have PREN ≥ 40 .

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادر کننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	شماره صفحه : ۱۸ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

6. CORROSION ASSESSMENT

6.1 GENERAL

The basis of temperature and pressure for corrosion calculations were taken from H&MB data in Process Flow Diagrams referred in clause 3.3.

6.2 CORROSIVE SPECIES: CO₂ AND H₂S

The corrosive species for Binak B/C Manifold Extension are provided in ATTACHMENT 1 as Summary of ECE 5.4 corrosion results. This software considers oil gravity, water cut, flow rate, temperature, and pressure and design life.

6.3 CORROSION ASSESSMENT – UNINHIBITED FLUID

The material selection for the lines first examines the suitability of carbon steel. Carbon steel in some streams will be used with inhibitor and in some streams will be used without inhibitor.

6.4 CORROSION MONITORING PHILOSOPHY



The reliability of both the materials selection and the corrosion assessment need to be verified at site through monitoring and careful inspection during every plant/equipment shutdown. The Risk Based Inspection plan should be developed by the plant during operation in order to know where, when and how to inspect taking into account the mutual interdependence between the various section of the plant.

The following methods of corrosion monitoring will be considered. In the direct methods the actual metal loss is being measured. With the indirect techniques except the iron count the measurement is on the test coupon.

Visual inspection is particularly desirable at equipment locations and weld joints susceptible to accelerated attack. Where visual inspection should be combined with other measurements, ultrasonic inspection and callipers can be used. Removable spool can be provided at critical vessels nozzles and inspection at the nozzles and spools will be provided valuable information concerning any corrosion related problems.

Ultrasonic inspection in conjunction with radiography is proposed as the primary means of monitoring and detection corrosion. Base line inspection should be conducted and documented. The location of these inspections should be determined based on susceptibility to corrosion and accessibility during operation and maintenance. The detailed locations will be decided during detailed stage.

Following the baseline inspection, period inspections should be performed and the maximum interval should be 5 years for carbon steel lines and 10 years for CRA lines. Subsequent inspection shall be based on comparing the actual calculated corrosion rate with the predicted the

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های رو زمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادر کننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	شماره صفحه : ۱۹ از ۲۵
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

corrosion rates. The subsequent duration for inspection should not exceed half the remaining life of the line.

Direct	Indirect
Visual inspection	Iron counts/Coupons
Ultrasonic Inspection	Linear Polarization Probe
Callipers	Electrical Resistance probe
Test Spools	Galvanic Probe
Radiography	Hydrogen Probe
	Bio-Probe

A formal review of the corrosion monitoring requirements shall be carried out as a part of the detailed design.

In this project corrosion probe & coupon at inlet of manifold and periodic measurement of pipe thickness must be considered. Also, creation of low points and dead points must be avoided much as possible .

7. HYDROCARBON , WATER CHARACTERISTICS

The following indicates the content of hydrocarbon composition & specifications in hydrocarbon fluids:



7.1 OIL COMPOSITION

Process condition of new headers such as temperature, pressure, corrosive agents, hydrocarbon and water flows and water analysis has been summarized in section 9 (Attachment).

7.2 FORMATION WATER

Water Analysis in Oil Specification

ION	Na ⁺	Ca ²⁺	Mg ²⁺	Cl ⁻	SO ₄ ²⁻	CO ₃ ²⁻
ppm	65299	10720	1312	123185	300	415

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های رو زمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>								
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه : ۲۰ از ۲۵	
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال		نسخه
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	

8. RECOMMENDATION

8.1 PROCESS EQUIPMENT



Wellhead Flow line No.	Tag No.	Equipment	Body Material/Fixed Internals	Corrosion Allowance (mm)	NACE MR0175 REQUIREMENTS	Lining / Cladding
W018S	ST-101	Stone Trap	K.C.S	6	Yes	-
W008N	ST-1601	Stone Trap	K.C.S	6	Yes	-
W046S	ST-1301	Stone Trap	K.C.S	6	Yes	-
W028	ST-1401	Stone Trap	K.C.S	6	Yes	-
W035	ST-1501	Stone Trap	K.C.S	6	Yes	-
W007S	ST-1201	Stone Trap	K.C.S	6	Yes	-

8.2 PROCESS PIPING

Lines corrosion circuit is comprised as below table with the results ECE 5.4 software (Section 9- Attachments). So results of predict ECE 5.4 been considered as the basis of material selection. The results of this software are in this section.

The ECE 5.4 program predicts acceptable general Corrosion rate and pitting corrosion risk in wellhead and flow lines. This software specifies NACE MR 0175/ISO15156 regions accurately.



As attached water cut trend, wells contain 15% in most of design life. Hence corrosion calculation has been carried out using ECE 5.4 for these water cuts as below table:

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>								
شماره پیمان:	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT							شماره صفحه : ۲۱ از ۲۵	
۰۵۳ - ۰۷۳ - ۹۱۸۴	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال		نسخه
	BK	SSGRL	PEDCO	110	PI	RT	0001		D04

LINES CORROSION CIRCUIT for WH Facilities



Wellhead Flow line No. / WaterCut		Years		Press. (Bara) @ Inlet S/W		Temp. (°C) @ Inlet S/W		ECE Results (Summer)			ECE Results (Winter)			Corrosion mm/ Years	Selected Material+ Corrosion Allowance	NACE MR 0175 /ISO1 5156
								Liquid Velocity m/s	General Corr. (mm/Yr)	Sour Pitting Rate (mm/Yr)	Liquid Velocity m/s	General Corr. (mm/Yr.)	Sour Pitting Rate (mm/Yr)			
W008N	0%	1401	1	44.8	44.8	75.0	75.0	0.19	0.03	0.59	0.19	0.03	0.59	0.03	C.S+6mm	Yes
	1%	1402	1	44.8	44.8	75.0	75.0	0.19	0.03	0.60	0.19	0.03	0.60	0.03		
	2%	1403	1	44.8	44.8	75.0	75.0	0.19	0.03	0.59	0.19	0.02	0.59	0.03		
	3%	1404	1	44.8	44.8	75.0	75.0	0.20	0.03	0.60	0.20	0.03	0.60	0.03		
	5%	1405	1	44.8	44.8	75.0	75.0	0.20	0.03	0.61	0.20	0.03	0.61	0.03		
	10%	1406	1	44.8	44.8	75.0	75.0	0.21	0.03	0.62	0.21	0.03	0.62	0.03		
	12%	1407	1	44.8	44.8	75.0	75.0	0.21	0.03	0.62	0.21	0.03	0.62	0.03		
	13%	1408	1	44.8	44.8	75.0	75.0	0.21	0.03	0.62	0.21	0.03	0.62	0.03		
	14%	1409	1	44.8	44.8	75.0	75.0	0.22	0.03	0.62	0.22	0.03	0.62	0.03		
	15%	1410 to 1420	11	44.8	44.8	75.0	75.0	0.22	0.03	0.63	0.22	0.03	0.63	0.33		
Total		1401 to 1420	20											0.60		

Wellhead Flow line No. / WaterCut		Years		Press. (Bara) @ Inlet S/W		Temp. (°C) @ Inlet S/W		ECE Results (Summer)			ECE Results (Winter)			Corrosion mm/ Years	Selected Material+ Corrosion Allowance	NACE MR 0175 /ISO1 5156
								Liquid Velocity m/s	General Corr. (mm/Yr)	Sour Pitting Rate (mm/Yr)	Liquid Velocity m/s	General Corr. (mm/Yr.)	Sour Pitting Rate (mm/Yr)			
W018S	0%	1401	1	44.8	44.8	75.0	75.0	0.19	0.03	0.59	0.19	0.03	0.59	0.03	C.S+6mm	Yes
	1%	1402	1	44.8	44.8	75.0	75.0	0.19	0.03	0.60	0.19	0.03	0.60	0.03		
	2%	1403	1	44.8	44.8	75.0	75.0	0.20	0.03	0.60	0.20	0.03	0.60	0.03		
	3%	1404	1	44.8	44.8	75.0	75.0	0.20	0.03	0.60	0.20	0.03	0.60	0.03		
	5%	1405	1	44.8	44.8	75.0	75.0	0.20	0.03	0.61	0.20	0.03	0.61	0.03		
	10%	1406	1	44.8	44.8	75.0	75.0	0.21	0.03	0.62	0.21	0.03	0.62	0.03		
	12%	1407	1	44.8	44.8	75.0	75.0	0.21	0.03	0.62	0.21	0.03	0.62	0.03		
	13%	1408	1	44.8	44.8	75.0	75.0	0.21	0.03	0.62	0.21	0.03	0.62	0.03		
	14%	1409	1	44.8	44.8	75.0	75.0	0.22	0.03	0.62	0.22	0.03	0.62	0.03		
	15%	1410 to 1420	11	44.8	44.8	75.0	75.0	0.22	0.03	0.63	0.22	0.03	0.63	0.33		
Total		1401 to 1420	20											0.60		

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های رو زمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>								
شماره پیمان: ۰۵۳ - ۰۷۳ - ۹۱۸۴	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								شماره صفحه : ۲۲ از ۲۵
	پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	
	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	



Wellhead Flow line No. / WaterCut		Years		Press. (Bara) @ Inlet S/W		Temp. (°C) @ Inlet S/W		ECE Results (Summer)			ECE Results (Winter)			Corrosion mm/ Years	Selected Material+ Corrosion Allowance	NACE MR 0175 /ISO1 5156
								Liquid Velocity m/s	General Corr. (mm/Yr)	Sour Pitting Rate (mm/Yr)	Liquid Velocity m/s	General Corr. (mm/Yr.)	Sour Pitting Rate (mm/Yr)			
W007	3%	1401	1	44.8	44.8	80.0	80.0	0.25	0.03	0.97	0.25	0.03	0.97	0.03	C.S+6mm	Yes
	4%	1402	1	44.8	44.8	80.0	80.0	0.25	0.03	0.97	0.25	0.03	0.97	0.03		
	5%	1403	1	44.8	44.8	80.0	80.0	0.25	0.03	0.97	0.25	0.03	0.97	0.03		
	7%	1404	1	44.8	44.8	80.0	80.0	0.26	0.03	0.98	0.26	0.03	0.98	0.03		
	10%	1405	1	44.8	44.8	80.0	80.0	0.26	0.04	0.98	0.26	0.04	0.98	0.04		
	12%	1406	1	44.8	44.8	80.0	80.0	0.26	0.04	0.99	0.26	0.04	0.99	0.04		
	15%	1407 to 1411	5	44.8	44.8	80.0	80.0	0.27	0.04	1.00	0.27	0.04	1.00	0.20		
	25%	1412 to 1413	2	44.8	44.8	80.0	80.0	0.28	0.04	1.03	0.28	0.04	1.03	0.08		
	30%	1414 to 1415	2	44.8	44.8	80.0	80.0	0.29	0.04	1.04	0.29	0.04	1.04	0.08		
	35%	1416 to 1417	2	44.8	44.8	80.0	80.0	0.30	0.04	1.06	0.30	0.04	1.06	0.08		
40%	1418 to 1420	3	44.8	44.8	80.0	80.0	0.32	0.04	1.08	0.32	0.04	1.08	0.12			
Total		1401 to 1420	20											0.76		

Wellhead Flow line No. / WaterCut		Years		Press. (Bara) @ Inlet S/W		Temp. (°C) @ Inlet S/W		ECE Results (Summer)			ECE Results (Winter)			Corrosion mm/ Years	Selected Material+ Corrosion Allowance	NACE MR 0175 /ISO1 5156
								Liquid Velocity m/s	General Corr. (mm/Yr)	Sour Pitting Rate (mm/Yr)	Liquid Velocity m/s	General Corr. (mm/Yr.)	Sour Pitting Rate (mm/Yr)			
W028	3%	1401	1	44.8	44.8	80.0	80.0	0.63	0.07	1.91	0.63	0.07	1.91	0.07	C.S+6mm	Yes
	4%	1402	1	44.8	44.8	80.0	80.0	0.63	0.07	1.91	0.63	0.07	1.91	0.07		
	5%	1403	1	44.8	44.8	80.0	80.0	0.63	0.07	1.91	0.63	0.07	1.92	0.07		
	7%	1404	1	44.8	44.8	80.0	80.0	0.64	0.07	1.92	0.64	0.07	1.92	0.07		
	10%	1405	1	44.8	44.8	80.0	80.0	0.65	0.07	1.93	0.65	0.07	1.93	0.07		
	12%	1406	1	44.8	44.8	80.0	80.0	0.66	0.07	1.94	0.66	0.07	1.94	0.07		
	15%	1407 to 1411	5	44.8	44.8	80.0	80.0	0.67	0.07	1.96	0.67	0.07	1.96	0.35		
	25%	1412 to 1413	2	44.8	44.8	80.0	80.0	0.71	0.07	2.01	0.71	0.07	2.01	0.14		
	30%	1414 to 1415	2	44.8	44.8	80.0	80.0	0.73	0.07	2.03	0.73	0.07	2.03	0.14		
	35%	1416 to 1417	2	44.8	44.8	80.0	80.0	0.76	0.08	2.07	0.76	0.08	2.07	0.16		
40%	1418 to 1420	3	44.8	44.8	80.0	80.0	0.79	0.08	2.10	0.79	0.08	2.10	0.24			
Total		1401 to 1420	20											1.45		

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های روزمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																	
شماره پیمان:	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT	شماره صفحه: ۲۳ از ۲۵																
۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><td>پروژه</td><td>بسته کاری</td><td>صادرکننده</td><td>تسهیلات</td><td>رشته</td><td>نوع مدرک</td><td>سریال</td><td>نسخه</td></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	پروژه	بسته کاری	صادرکننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	
پروژه	بسته کاری	صادرکننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه											
BK	SSGRL	PEDCO	110	PI	RT	0001	D04											

Wellhead Flow line No. / WaterCut		Years		Press. (Bara) @ Inlet S/W		Temp. (°C) @ Inlet S/W		ECE Results (Summer)			ECE Results (Winter)			Corrosion mm/ Years	Selected Material+ Corrosion Allowance	NACE MR 0175 /ISO1 5156
								Liquid Velocity m/s	General Corr. (mm/Yr)	Sour Pitting Rate (mm/Yr)	Liquid Velocity m/s	General Corr. (mm/Yr.)	Sour Pitting Rate (mm/Yr)			
W035	3%	1401	1	44.8	44.8	80.0	80.0	0.63	0.07	1.91	0.63	0.07	1.91	0.07	C.S+6mm	Yes
	4%	1402	1	44.8	44.8	80.0	80.0	0.63	0.07	1.91	0.63	0.07	1.91	0.07		
	5%	1403	1	44.8	44.8	80.0	80.0	0.63	0.07	1.91	0.63	0.07	1.91	0.07		
	7%	1404	1	44.8	44.8	80.0	80.0	0.64	0.07	1.92	0.64	0.07	1.92	0.07		
	10%	1405	1	44.8	44.8	80.0	80.0	0.65	0.07	1.93	0.65	0.07	1.93	0.07		
	12%	1406	1	44.8	44.8	80.0	80.0	0.66	0.07	1.94	0.66	0.07	1.94	0.07		
	15%	1407 to 1411	5	44.8	44.8	80.0	80.0	0.67	0.07	1.96	0.67	0.07	1.96	0.35		
	25%	1412 to 1413	2	44.8	44.8	80.0	80.0	0.71	0.07	2.01	0.71	0.07	2.01	0.14		
	30%	1414 to 1415	2	44.8	44.8	80.0	80.0	0.73	0.07	2.03	0.73	0.07	2.03	0.14		
	35%	1416 to 1417	2	44.8	44.8	80.0	80.0	0.76	0.08	2.07	0.76	0.08	2.07	0.16		
40%	1418 to 1420	3	44.8	44.8	80.0	80.0	0.79	0.08	2.10	0.79	0.08	2.10	0.24			
Total		1401 to 1420	20											1.45		

Wellhead Flow line No. / WaterCut		Years		Press. (Bara) @ Inlet S/W		Temp. (°C) @ Inlet S/W		ECE Results (Summer)			ECE Results (Winter)			Corrosion mm/ Years	Selected Material+ Corrosion Allowance	NACE MR 0175 /ISO1 5156
								Liquid Velocity m/s	General Corr. (mm/Yr)	Sour Pitting Rate (mm/Yr)	Liquid Velocity m/s	General Corr. (mm/Yr.)	Sour Pitting Rate (mm/Yr)			
W046	3%	1401	1	44.8	44.8	80.0	80.0	0.38	0.05	1.31	0.38	0.05	1.31	0.05	C.S+6mm	Yes
	4%	1402	1	44.8	44.8	80.0	80.0	0.38	0.05	1.32	0.38	0.05	1.32	0.05		
	5%	1403	1	44.8	44.8	80.0	80.0	0.38	0.05	1.32	0.38	0.05	1.32	0.05		
	7%	1404	1	44.8	44.8	80.0	80.0	0.38	0.05	1.32	0.38	0.05	1.32	0.05		
	10%	1405	1	44.8	44.8	80.0	80.0	0.39	0.05	1.33	0.39	0.05	1.33	0.05		
	12%	1406	1	44.8	44.8	80.0	80.0	0.39	0.05	1.34	0.39	0.05	1.34	0.05		
	15%	1407 to 1411	5	44.8	44.8	80.0	80.0	0.40	0.05	1.35	0.40	0.05	1.35	0.25		
	25%	1412 to 1413	2	44.8	44.8	80.0	80.0	0.42	0.05	1.39	0.42	0.05	1.39	0.10		
	30%	1414 to 1415	2	44.8	44.8	80.0	80.0	0.44	0.05	1.41	0.44	0.05	1.41	0.10		
	35%	1416 to 1417	2	44.8	44.8	80.0	80.0	0.46	0.05	1.43	0.46	0.05	1.43	0.10		
40%	1418 to 1420	3	44.8	44.8	80.0	80.0	0.47	0.05	1.46	0.47	0.05	1.46	0.15			
Total		1401 to 1420	20											1.00		

	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های رو زمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																									
<p>شماره پیمان:</p> <p>۰۵۳ - ۰۷۳ - ۹۱۸۴</p>	<table><tr><th colspan="8">PIPING CORROSION STUDY & MATERIAL SELECTION REPORT</th></tr><tr><th>پروژه</th><th>بسته کاری</th><th>صادر کننده</th><th>تسهیلات</th><th>رشته</th><th>نوع مدرک</th><th>سریال</th><th>نسخه</th></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT								پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04	<p>شماره صفحه : ۲۴ از ۲۵</p>
PIPING CORROSION STUDY & MATERIAL SELECTION REPORT																										
پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه																			
BK	SSGRL	PEDCO	110	PI	RT	0001	D04																			

LINES CORROSION CIRCUIT for Manifold Facilities

Stream No.	Press. (Bara)	Temp. (°C) S/W	ECE Results (Summer)			ECE Results (Winter)			Corrosion mm/ 20 years	Selected Material+ Corrosion Allowance	NACE MR 0175 / Region	Notes
			Liquid Velocity m/s	General Corr. (mm/Yr)	Sour Pitting Risk	Liquid Velocity m/s	General Corr. (mm/Yr.)	Sour Pitting Risk				
New Header	11.8	47.6/37.2	3.51	0.02	Mod.	3.31	0.01	Mod.	0.40	C.S+3 mm	Region 1	Note 1
1	13.8	36.5/22.1	0.42	0.02	High	0.39	0.02	High	0.40	C.S+3 mm	Region 1	Note 1
2	11.8	36.3/22.0	0.47	0.02	High	0.46	0.01	High	0.40	C.S+3 mm	Region 1	Note 1
3	13.8	36.0/23.6	2.09	0.01	Mod.	1.95	0.01	Mod.	0.20	C.S+3 mm	Region 1	Note 1
4	11.8	35.5/23.1	2.71	0.01	Mod.	2.41	0.01	Mod.	0.20	C.S+3 mm	Region 1	Note 1
5	13.8	42.7/29.8	0.43	0.02	High	0.40	0.02	High	0.40	C.S+3 mm	Region 1	Note 1
6	11.8	42.5/29.7	0.49	0.02	High	0.46	0.02	High	0.40	C.S+3 mm	Region 1	Note 1
7	13.8	55.0/46.5	3.87	0.03	Mod.	3.70	0.02	Mod.	0.60	C.S+3 mm	Region 1	Note 1
8	11.8	54.4/46.0	4.45	0.03	Mod.	4.25	0.02	Mod.	0.60	C.S+3 mm	Region 1	Note 1
9	13.8	51.0/41.2	3.79	0.02	Mod.	3.59	0.02	Mod.	0.40	C.S+3 mm	Region 1	Note 1
10	11.8	50.5/47.7	4.36	0.03	Mod.	4.13	0.02	Mod.	0.60	C.S+3 mm	Region 1	Note 1
11	13.8	52.0/41.7	1.52	0.01	Mod.	1.44	0.01	Mod.	0.20	C.S+3 mm	Region 1	Note 1
12	11.8	51.5/41.3	1.71	0.01	Mod.	1.66	0.01	Mod.	0.20	C.S+3 mm	Region 1	Note 1

- 1- Since the headers are extension of existing manifold, the material and piping class of existing lines should be followed. There is Pitting probability only in the stream numbers 1,2,5,6. With considering of liquid Velocity of header (3.31 m/s), pitting will not be so high. With periodic witness and measurements of thickness for these lines, it is recommended to keep 3 mm corrosion allowance and no changes is required in the design of these lines.



8.3 UTILITY PIPING



Materials for utility equipment and piping are selected on the basis of common hydrocarbon industry practice and in line with IPS standard.

8.3.1. Drains

Based on calculation for main headers, Carbon Steel (NACE) + with 3 mm is considered for closed drain piping.

8.3.2. Non- Hydrocarbon Utility Systems

The material for the non-hydrocarbon utility pipe work is selected according to standard industry practice. Following table provides its summary (if any):

 NISOC	<p>نگهداشت و افزایش تولید میدان نفتی بینک</p> <p>فعالیت های رو زمینی در بسته های کاری تحت الارض</p> <p>عمومی و مشترک</p>																	
شماره پیمان:	PIPING CORROSION STUDY & MATERIAL SELECTION REPORT	شماره صفحه : ۲۵ از ۲۵																
۰۵۳ - ۰۷۳ - ۹۱۸۴	<table><tr><td>پروژه</td><td>بسته کاری</td><td>صادر کننده</td><td>تسهیلات</td><td>رشته</td><td>نوع مدرک</td><td>سریال</td><td>نسخه</td></tr><tr><td>BK</td><td>SSGRL</td><td>PEDCO</td><td>110</td><td>PI</td><td>RT</td><td>0001</td><td>D04</td></tr></table>		پروژه	بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه	BK	SSGRL	PEDCO	110	PI	RT	0001	D04
	پروژه		بسته کاری	صادر کننده	تسهیلات	رشته	نوع مدرک	سریال	نسخه									
BK	SSGRL	PEDCO	110	PI	RT	0001	D04											

UTILITY PIPING SYSTEMS (NON-HYDROCARBON)

Piping System	Material	CA (mm)
Fuel Gas, Fire water	Carbon Steel	3
Potable Water	Galv. Carbon Steel /HDPE	0
Fire Water (UG)	HDPE	0
Chemical	S.S 316L	0
Instrument Air	Galv. Carbon Steel	0

Note:

- Underground utility water piping systems shall be polyethylene.
- The manufacturer of the HDPE pipes shall obtain all health approvals from the relevant authorities.

9. ATACHMENTS

ECE 5.4 original files, PFD, Simulation Report, and P&ID are attached to this document to support the results.